

Diamond Plate Conductive Runner Mats

Specification Sheet



Performance	Best
Uses	Dry areas at risk for damage from static electricity
Compound	Vinyl
Coefficient of Friction	0.68 Dry per ASTM F1677
Tabor Abrasion	1% lost @ 1,000 cycles per Fed. Std. 191
Flammability	"A" Rating per MVSS 302
Warranty	1 years
Wear Resistance	4.5
Slip Resistance	3.5
Conductivity	4
MNF	65
Thickness	5/32"
Resistivity	RTT: 1×10^4 to 5×10^5 Ohms