

Smooth Top Conductive Runner Mats

Specification Sheet



Performance	Best
Uses	Dry areas at risk for damage from static electricity
Compound	Vinyl / SBR Rubber
Coefficient of Friction	0.68 / 0.78 Dry per ASTM F1677
Tabor Abrasion	1% lost @ 1,000 cycles per Fed. Std. 191
Flammability	"A" Rating per MVSS 302
Warranty	1 years
Wear Resistance	4.5
Slip Resistance	4
Conductivity	5
MNF	65
Thickness	3/32"
Resistivity	RTT: 1×10^4 to 5×10^5 Ohms